



# G-PAEK™ 1200G

**Product Details:** Ultra high Performance thermoplastic polymer, virgin, semicrystalline granules suitable for cast film extrusion, easy flow, Beige in color.

**Application Areas:** Suitable for high temperature applications, high wear & abrasion resistance, high chemical resistance is required & for metal replacement with plastics etc.

## Typical Properties:

PROPERTY	TEST METHOD/CONDITIONS	UNIT	G-PAEK™ 1200G
<b>General Properties</b>			
Density	23°C	g/cc	1.30
Water Absorption	ASTM D 570-98	%	0.07
Rockwell Hardness	ASTM D 785/M Scale	-	98
Shore D Hardness	ASTM D 2240-05	-	87
Mold Shrinkage (400°C nozzle, 210°C Mold)	Along Flow	%	1.0
	Across Flow	%	1.3
Spiral Flow (400°C nozzle, 220°C Mold)	ASTM D 3123, 2 mm	mm	408

<b>Thermal Properties</b>			
Glass Transition Temperature(Tg)	ASTM D 3418	°C	152
Melting Point (Tm)	ASTM D 3418	°C	372
Heat Deflection Temperature (HDT)	ASTM D 648 /1.8 MPa	°C	175
Continuous Use Temperature ( Expected)	UL 746B	°C	280

<b>Mechanical Properties at 23°C</b>			
Tensile Strength	ASTM D 638	MPa	110
Tensile Modulus	ASTM D 638	GPa	4.2
Elongation at Break	ASTM D 638	%	10-15
Flexural Strength	ASTM D 790	MPa	185
Flexural Modulus	ASTM D 790	GPa	4.1
Compressive Strength	ASTM D 695	MPa	135
Izod Impact Strength(Notched)	ASTM D 256	J/m	60
Izod Impact Strength(Un-notched)	ASTM D 256	J/m	No Break



PROPERTY	TEST METHOD/CONDITIONS	UNIT	G-PAEK™ 1200G
<b>Rheological Properties</b>			
Melt Viscosity at 400°C	ASTM D 3835/@1000 s <sup>-1</sup>	Pa.s	250-300

<b>Electrical Properties</b>			
Dielectric Strength	ASTM D 149/ 3.2mm thickness	Kvmm <sup>-1</sup>	17
Surface Resistivity	ASTM D 257	Ω	10 <sup>16</sup>
Volume Resistivity	ASTM D 257	Ωcm <sup>-1</sup>	10 <sup>16</sup>
Arc Resistance	ASTM D 495/@ 500 Volts	Sec	175
CTI	ASTM D 3638	V/50 drops	145

<b>Fire Properties</b>			
Flammability	UL 94/0.8 mm	-	V-0

<b>Recommended Processing Conditions</b>	
Drying Temperature/Time	4-6 hrs at 150°C
Temperature Settings	390-400°C
Nozzle Temperature	400°C
Hopper/ Throat Temperature	60-80°C
Mold Temperature	200-220°C

<b>Nominal Granule Size</b>
• Dimensions, length 2.0 – 4.0 mm, diameter 2.0 – 3.5 mm
• No longs greater than 8.0 mm
• Granules of uniform cut and color

THE INFORMATION PROVIDED IN THIS DATA SHEET CORRESPONDS TO OUR KNOWLEDGE ON THE SUBJECT AT THE DATE OF ITS PUBLICATION. THIS INFORMATION MAY BE SUBJECT TO REVISION AS NEW KNOWLEDGE AND EXPERIENCE BECOMES AVAILABLE. THE DATA PROVIDED FALL WITHIN THE NORMAL RANGE OF PRODUCT PROPERTIES AND RELATE ONLY TO THE SPECIFIC MATERIAL DESIGNATED; THESE DATA MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS, ADDITIVES OR PIGMENTS OR IN ANY PROCESS, UNLESS EXPRESSLY INDICATED OTHERWISE. THE DATA PROVIDED SHOULD NOT BE USED TO ESTABLISH SPECIFICATION LIMITS OR USED ALONE AS THE BASIS OF DESIGN; THEY ARE NOT INTENDED TO SUBSTITUTE FOR ANY TESTING YOU MAY NEED TO CONDUCT TO DETERMINE FOR YOURSELF THE SUITABILITY OF A SPECIFIC MATERIAL FOR YOUR PARTICULAR PURPOSES. SINCE GHARDA PLASTICS CANNOT ANTICIPATE ALL VARIATIONS IN ACTUAL END-USE CONDITIONS GHARDA PLASTICS MAKES NO WARRANTIES AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. NOTHING IN THIS PUBLICATION IS TO BE CONSIDERED AS A LICENSE TO OPERATE UNDER OR A RECOMMENDATION TO INFRINGE ANY PATENT RIGHTS. GHARDA PLASTICS ADVISES YOU TO SEEK INDEPENDENT COUNSEL FOR A FREEDOM TO PRACTICE OPINION ON THE INTENDED APPLICATION OR END-USE OF OUR PRODUCTS. FOR FURTHER INFORMATION, PLEASE CONTACT YOUR GHARDA PLASTICS REPRESENTATIVE

